

測試報告

Test Report

號碼(No.) : CT/2016/20529

日期(Date) : 2016/03/01

頁數(Page) : 1 of 3

彩麗薄膜股份有限公司

MAGICAL FILM ENTERPRISE CO., LTD.

台中市梧棲區永興路二段378巷36號

NO. 36, LANE 378, SEC. 2, YOUNGSING RD., WUQI DIST., TAICHUNG CITY 435, TAIWAN



以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by/on behalf of the applicant as) :

送樣廠商(Sample Submitted By) : 彩麗薄膜股份有限公司 (MAGICAL FILM ENTERPRISE CO., LTD.)
樣品名稱(Sample Description) : PET FILM (PET薄膜)
樣品材質(Sample Material) : PET
收件日期(Sample Receiving Date) : 2016/02/22
測試期間(Testing Period) : 2016/02/22 TO 2016/03/01

測試需求(Test Requested) :

依據客戶指定, 參考美國聯邦法規之藥物暨食品管理(FDA)-21 CFR 177.1630(使用條件e)進行測試。 測試項目請參閱測試結果表格。 / As specified by client, with reference to U. S. Food and Drug Administration (FDA) 21 CFR 177.1630 (Condition of use e) to conduct test. Please refer to result table for testing item(s).

測試結果(Test Results) : 請見下一頁 (Please refer to next pages).



George Fong / Supervisor
Signed for and on behalf of
SGS TAIWAN LTD.
Chemical Laboratory - Taipei

測試報告

Test Report

號碼(No.) : CT/2016/20529

日期(Date) : 2016/03/01

頁數(Page) : 2 of 3

彩麗薄膜股份有限公司

MAGICAL FILM ENTERPRISE CO., LTD.

台中市梧棲區永興路二段378巷36號

NO. 36, LANE 378, SEC. 2, YOUNGSING RD., WUQI DIST., TAICHUNG CITY 435, TAIWAN



測試結果(Test Results)

測試部位(PART NAME)No. 1 : 透明塑膠膜 (TRANSPARENT PLASTIC FILM)

通過(PASS)

測試項目 (Test Items)	單位 (Unit)	測試方法 (Method)	方法偵測 極限值 (MDL)	結果 (Result)	限值 (Limit)
				No. 1	
可溶於氯仿的萃取物 (水, 120°F, 24小時) / Chloroform-soluble extractives (D.I.-Water, 120°F, 24 hours)	mg/in ²	參考美國聯邦法規(CFR) Title 21, Pt 177.1630 (e). / With reference to CFR Title 21, Pt 177.1630 (e).	0.1	n. d.	0.5
可溶於氯仿的萃取物 (正庚烷, 120°F, 24小時) / Chloroform-soluble extractives (n-Heptane, 120°F, 24 hours)	mg/in ²	參考美國聯邦法規(CFR) Title 21, Pt 177.1630 (e). / With reference to CFR Title 21, Pt 177.1630 (e).	0.1	n. d.	0.5
可溶於氯仿的萃取物 (8% 酒精, 120°F, 24小時) / Chloroform-soluble extractives (8% alcohol, 120°F, 24 hours)	mg/in ²	參考美國聯邦法規(CFR) Title 21, Pt 177.1630 (e). / With reference to CFR Title 21, Pt 177.1630 (e).	0.1	n. d.	0.5

備註(Note) :

- 0.1wt% = 1000ppm ; mg/kg = ppm
- MDL = Method Detection Limit (方法偵測極限值)
- n. d. = Not Detected = less than MDL (未檢出)

測試報告

Test Report

號碼(No.) : CT/2016/20529

日期(Date) : 2016/03/01

頁數(Page) : 3 of 3

彩麗薄膜股份有限公司

MAGICAL FILM ENTERPRISE CO., LTD.


台中市梧棲區永興路二段378巷36號

NO. 36, LANE 378, SEC. 2, YOUNGSING RD., WUQI DIST., TAICHUNG CITY 435, TAIWAN



* 照片中如有箭頭標示，則表示為實際檢測之樣品/部位。*
(The tested sample / part is marked by an arrow if it's shown on the photo.)

CT/2016/20529



** 報告結尾 (End of Report) **

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Termse-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.